

Bengalac Woodprimer

Product description

Type

This product is a high quality primer. Based on alkyd resin.

Features and benefits

Easy application. Free from harmful heavy metals such as Mercury, Lead, Cadmium, Arsenic, Chromium etc.

Recommended use

Ideal as an undercoat for alkyd topcoats.

Substrate

Wood

Product data

Packaging size	4 L and 18L		
Colours	White		
Solids	47	± 2	volume% Theoretical
Specific gravity	1,4	kg/l	Theoretical
Flash point	Closed cup: 36°C (96,8°F)		
VOC	400	g/l	ISO 11890 EU

Application data

The product can be applied by

Roller : Recommended.

Spray : Use airless spray or conventional spray.

Brush : Recommended to paint corners and edges.

Guiding data for airless spray

Nozzle tip	0.018-0.021"
Spray angle degrees	65-80°
Pressure at nozzle	150 Kg/cm ² (2100 psi)

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Recommended film thickness per coat

Dry	Minimum	30 µm
Dry	Maximum	40 µm
Dry	Typical	35 µm
Wet	Minimum	65 µm
Wet	Maximum	85 µm
Wet	Typical	75 µm

Film thickness will vary and is calculated as average.

Spreading rate per coat

Theoretical	Minimum	11,75 m ² /l
Theoretical	Maximum	15,7 m ² /l
Theoretical	Typical	13,4 m ² /l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Thinner

Jotun Thinner No. 2

Dilution

Maximum 10 %

Cleaning of painting tools

Jotun Thinner No. 2

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

Relative Humidity (RH)	50 %	50 %	50 %
Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	16 h	8 h	6 h
Hard dry	48 h	24 h	18 h
Dried to over coat, minimum	48 h	24 h	18 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of foam release agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Bengalac Woodprimer : 1 Coat

Filler

Stucco : 2 Coats

Topcoat

Fenomastic topcoats or Bengalac Gloss or Bengalac Matt or Bengalac Semigloss : 2 Coats

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health- and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.