

Technical Data

Spontan Varnish



Product description

Spontan Varnish is a clear varnish based on urethane alkyd

Recommended use

Protection of interior and exterior wood work.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	25	50	35
Film thickness, wet (μm)	60	120	85
Theoretical spreading rate (m^2/l)	16,4	8,2	11,7

Physical properties

Colour	Transparent
Solids (vol %)*	41 \pm 2
Flash point	36°C \pm 2 (Setaflash)
Gloss	Glossy
Gloss retention	Very good
Water resistance	Good
Abrasion resistance	Good
Flexibility	Good

*Measured according to ISO 3233:1998 (E)

Surface preparation

Clean and dry surface. Surface contamination is to be removed by detergents and fresh water cleaning.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure correct drying.

Application methods

Spray	Use airless spray or conventional spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	Single pack.
Thinner/Cleaner	Jotun Thinner No. 2

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	5°C	10°C	23°C	40°C
Surface dry	3 h	2 h	1 h	0,5 h
Through dry	20 h	9 h	4 h	2 h
Dry to recoat, minimum	36 h	12 h	8 h	4 h
Dry to recoat, maximum ¹				

1. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Spontan Varnish 1 - 3 x 35 µm (Dry Film Thickness)

New wood-work should first be prepared with one coat Spontan Varnish thinned 10% with Jotun Thinner No. 2.

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

5 litre container

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 26 NOVEMBER 2010 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED