


Technical Information

Wanda EP Primer Grey / White 5:1 W2.05.02 APAC 24 Nov 2017



Suitable substrates	Existing Finishes, including thermoplastic acrylic finishes. Steel, etc Wanda Polyester Putties		
----------------------------	--	--	--

Surface preparation	Existing Finishes: Degrease and sand with P180-280 grit dry or P280-400 grit wet Bare Steel Surfaces: Degrease and sand with P80-180 grit dry Polyester Putties: Dry Sand with P180-280		
----------------------------	---	--	--

	Mixing Ratio	5 parts by volume: Wanda 5:1EP Greenish Grey (2 Pack) 1 part by volume: Wanda 5:1 EP Primer Hardener 3 parts by volume: Wanda 2K Thinner (any)	
---	---------------------	--	--

Viscosity	13-18 seconds using DIN #4 Cup		
------------------	--------------------------------	--	--

Pot life	8-10 hours at 30°C		
-----------------	--------------------	--	--

Spray gun set-up and application pressure	Gravity feed	1.5-2.0 mm	1.5-2.0 bar at the spray gun air inlet
--	--------------	------------	--

Application	Apply 2-3 full coats allowing 5-10 minutes flash-off between coats.		
--------------------	---	--	--

Film thickness	DFT: 25-30 µm per coat		
-----------------------	------------------------	--	--

Drying time	Dust Free 10-15 mins at 30°C Dry to handle 3 hours at 30°C Dry sanding time overnight at 30°C		
--------------------	--	--	--

Theoretical coverage	276m ² /liter per micron. Note: The practical coverage depends on several factors, including shape of the construction, roughness of surface, method of application being used and conditions of application.		
-----------------------------	--	--	--

Cleaning of equipment	Use Wanda 2K Thinner (any).		
------------------------------	-----------------------------	--	--

Shelf life	In supplied condition when stored at 5-40°C Wanda 5:1EP Grey-24 months Wanda Epoxy 5:1 Hardener-12 months		
-------------------	---	--	--

Technical Information

Wanda EP Primer Grey / White 5:1
W2.05.02 APAC 24 Nov 2017



Akzo Nobel Car Refinishes (Singapore) Pte Ltd
Address: 3 Changi Business Park Vista, #05-01 Akzo Nobel House, Singapore 486051
Tel: +65 6635 5262

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com